



DuPont Teijin Films™

Welcome, Chris Pendlebury Current Language: **US**

[Logoff](#) |
 [Welcome Page](#) |
 [Film Type Selector](#) |
 [Market Locator](#) |
 [Product Locator](#)

[Show Printable Version](#)

MELINEX® 462

DTF Only - Active

Product Description

Melinex® 462 is a high clarity polyester film manufactured with a coating on both surfaces that promotes adhesion to many solvent formulations and to most vinyl or acrylic base ink systems.

Typical Applications

Melinex® 462 is used in many general industrial applications where clarity and adhesion properties are critical, e.g., coating, lamination and print-on applications.

Typical Properties

Available Thickness [Gauge]
200; 265; 300; 380; 400; 460; 500; 650; 700; 1000

Property	Thickness	Value	Units	Test
OPTICAL				
Haze	200 - 500	1.0	% (Maximum)	ASTM D1003
Haze	650 - 700	1.5	% (Maximum)	ASTM D1003
Haze	1000	2.5	% (Maximum)	ASTM D1003
Total Light Transmission (TLT)	ALL	90	%	ASTM D1003
PHYSICAL				
C.O.F. (dynamic) A-B	ALL	0.70	(Maximum)	ASTM D1894
Tensile Strength MD	200 - 700	25,000	psi (Minimum)	ASTM D882A
Tensile Strength MD	1000	20,000	psi (Minimum)	ASTM D882A
Tensile Strength TD	200 - 700	25,000	psi (Minimum)	ASTM D882A
Tensile Strength TD	1000	20,000	psi (Minimum)	ASTM D882A
Yield (nominal)	200	9,918	in ² /lb	
Yield (nominal)	265	7,485	in ² /lb	
Yield (nominal)	300	6,612	in ² /lb	
Yield (nominal)	380	5,220	in ² /lb	
Yield (nominal)	460	4,312	in ² /lb	
Yield (nominal)	650	3,052	in ² /lb	
Yield (nominal)	700	2,800	in ² /lb	
Yield (nominal)	1000	1,984	in ² /lb	
Yield Strength MD	ALL	13,000	psi (Minimum)	ASTM D882A
Yield Strength TD	ALL	13,000	psi (Minimum)	ASTM D882A
THERMAL				
Shrinkage MD (190°C)	ALL	2.5	%	Unrestrained @ 190°C/5 min
Shrinkage TD (190°C)	ALL	1.0	%	Unrestrained @ 190°C/5 min

Contact Info

DuPont Teijin Films U.S. Limited Partnership
3600 Discovery Drive
Chester, VA 23836 USA
Tel: (800) 635-4639
Fax: (804) 530-9867

Disclaimer

Note: These values are typical performance data for DuPont Teijin Films' polyester film; they are not intended to be used as design data. We believe this information is the best currently available on the subject. It is offered as a possible helpful suggestion in experimentation you may care to undertake along these lines. It is subject to revision as additional knowledge and experience is gained. DuPont Teijin Films makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. This publication is not a license to operate under, or intended to suggest infringement of, any existing patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body ([DuPont Teijin Films Medical Policy](#)). For other medical applications, see the [Medical Caution Statement](#). DuPont Teijin Films accepts no liability for use of its products in medical applications not reviewed and approved by DuPont Teijin Films or for product misuse. DuPont Teijin Films supplies products to an agreed specification and does not manufacture products designed specifically for medical end use.

Melinex®, Mylar® and Melinex® ST™ are registered trademarks of DuPont Teijin Films U.S. Limited Partnership. Teijin® and Tetoron® are registered trademarks of Teijin Limited used under license by DuPont Teijin Films U.S. Limited Partnership. Teonex® is a registered trademark of Teijin DuPont Films Japan Limited and is used under license by DuPont Teijin Films U.S. Limited Partnership.



[Show Printable Version](#)

Copyright © 2006 DuPont Teijin Films. All rights reserved.
Developed and Powered by Client Centered Technologies, Inc.

Distributed by:



www.polymerfilms.com

Film East: Tyngsboro, MA | 978-226-0021
Film Central: Naperville, IL | 630-428-4350
Film West: Fresno, CA | 559-383-3456
Film Canada: Brampton, ON | 905-789-3100
Film Mexico: Apodaca, Nuevo León | 52-81-8369-4688