



# DuPont Teijin Films™

## MELINEX® 534

### Product Description

Melinex® 534 is an opaque white film with superb handling properties and a unique glossy appearance. It is pre-treated on both surfaces to promote adhesion to aqueous based inks and coatings.

### Typical Properties

<b>Available Thickness [Gauge]</b>
380

Property	Thickness	Value	Units	Test
<b>OPTICAL</b>				
Total Light Transmission (TLT)	380	13.0	%	ASTM D1003
<b>PHYSICAL</b>				
C.O.F. (dynamic) A-B	380	0.32		ASTM D1894
Elongation at Break MD	380	152	%	ASTM D882A
Elongation at Break TD	380	105	%	ASTM D882A
Tensile Strength MD (break)	380	20,000	psi	ASTM D882A
Tensile Strength MD 5%	380	12,100	psi	ASTM D882A
Tensile Strength TD (break)	380	23,400	psi	ASTM D882A
Tensile Strength TD 5%	380	12,400	psi	ASTM D882A
Yield (nominal)	380	5,200	in <sup>2</sup> /lb	
<b>THERMAL</b>				
Shrinkage MD (190°C)	380	0.7	%	Unrestrained @ 190°C/5 min
Shrinkage TD (190°C)	380	0.6	%	Unrestrained @ 190°C/5 min

### Disclaimer

Note: These values are typical performance data for DuPont Teijin Films' polyester film; they are not intended to be used as design data. We believe this information is the best currently available on the subject. It is offered as a possible helpful suggestion in experimentation you may care to undertake along these lines. It is subject to revision as additional knowledge and experience is gained. DuPont Teijin Films makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. This publication is not a license to operate under, or intended to suggest infringement of, any existing patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body ([DuPont Teijin Films Medical Policy](#)). For other medical applications, see the [Medical Caution Statement](#). DuPont Teijin Films accepts no liability for use of its products in medical applications not reviewed and approved by DuPont Teijin Films or for product misuse. DuPont Teijin Films supplies products to an agreed specification and does not manufacture products designed specifically for medical end use.

Melinex®, Mylar® and Melinex® ST™ are registered trademarks of DuPont Teijin Films U.S. Limited Partnership. Teijin® and Tetoron® are registered trademarks of Teijin Limited used under license by DuPont Teijin Films U.S. Limited Partnership. Teonex® is a registered trademark of Teijin DuPont Films Japan Limited and is used under license by DuPont Teijin Films U.S. Limited Partnership.

Distributed by:



[www.polymerfilms.com](http://www.polymerfilms.com)

**Film East:** Tyngsboro, MA | 978-226-0021  
**Film Central:** Naperville, IL | 630-428-4350  
**Film West:** Fresno, CA | 559-383-3456  
**Film Canada:** Brampton, ON | 905-789-3100  
**Film Mexico:** Apodaca, Nuevo León | 52-81-8369-4688