

ACRYLITE® Film 0F032 matt

Product Data Sheet

Product

ACRYLITE® Film 0F032 matt is a very high UV and weather resistant acrylic film with both side matt surfaces for graphic printings and high quality laminations.

The film maintains high light transmission properties even though it displays a matt surface. Therefore it is suitable to create matt finishing effects even after printing and lamination.

The matt finish provides an anti-blocking effect in printing processes and light scattering can be achieved when used in illumination applications.

The irreversible anti-glare surface of ACRYLITE® Film 0F032 is not affected by thermoforming or deep drawing.

Application

ACRYLITE® Film 0F032 matt can be used to be printed on as high quality film decoration and then laminated on different polymeric films and sheets. Laminated decoration films based on ACRYLITE® are suitable for a wide range of molding processes such as thermoforming and insert molding.

In labels, tapes and graphic arts, ACRYLITE® Film 0F032 matt can be used as a matt single face layer or matt overlay in laminate systems for high UV and weathering protection.

Due to its good anti-glare and matt surface ACRYLITE® 0F032 matt can be used as overlay in high quality ID Cards.

Processing

ACRYLITE® Film 0F032 has a good printability behavior in all printing technologies such as gravure, flexography and digital. In most of the cases any pre-treatment or primers are not required.

ACRYLITE® Film 0F032 can be laminated onto polymeric substrates such as films or extruded sheets based on PVC, PC, ABS, PMMA and ASA by in-line or roll-to-roll heat lamination.

High quality laminates in between ACRYLITE® Film 0F032 and other polymeric substrates such as PET, PC, PP, PE and PVC can be achieved with pressure sensitive adhesives (PSA) or solvent based adhesives.

The film can be cut-to-size or die cut.

Sales range

ACRYLITE® Film 0F032 matt is delivered in standard rolls of 70µm thickness, 1420mm width and 2050mm length.

Tailor made rolls can be produced under prior commercial agreement.

Technical data

Properties	Test method	Unit	Value
Optical			
Luminous transmittance τ_{D65}	ISO 13468-2	%	90
UV transmittance (280 - 380 nm)	DIN EN 410:2011	%	< 1
Gloss (60)°	DIN 67530		22
Mechanical			
Tensile stress at yield (σ_y)	ISO 527-3	MPa	35
Yield strain (ϵ_y)	ISO 527-3	%	6
Nominal strain at break (ϵ_b)	ISO 527-3	%	> 50
Thermal			
Glass transition temperature T_g (DSC)	ISO 11357	°C	88
Miscellaneous			
Accelerated weathering resistance	ISO 4892-2 method A, cycle 1, 65% RH	H	12000 No visible change
Specific gravity	DIN 53479	g/cm ³	1,13
Surface tension	DIN 53364	mN/m	50

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether expressed or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technical progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products should be used.

Evonik Industries is a worldwide manufacturer of PMMA products sold under the ACRYLITE® trademark in the Americas and under the PLEXIGLAS® trademark in the European, Asian, African, and Australian continents. ©Evonik Cyro LLC. All rights reserved.

Printed in the USA.

Distributed by:



www.polymerfilms.com

Film East: Tyngsboro, MA | 978-226-0021
Film Central: Naperville, IL | 630-428-4350
Film West: Fresno, CA | 559-383-3456
Film Canada: Brampton, ON | 905-789-3100
Film Mexico: Apodaca, Nuevo León | 52-81-8369-4688