

LEXAN™ 8B36 FILM

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ 8B36 film is a one side suede, one side matte transparent polycarbonate film. It offers high temperature resistance, excellent dimensional stability and good printability without pretreatment making it very suitable for multi-layer printing. The heavy suede texture offers mar resistance and the product can be used over light-emitting devices. Its low gloss level reduces glare in automobile interiors and offices.

TYPICAL PROPERTY VALUES

| PROPERTY | ASTM TEST METHOD | UNITS (USCS) | VALUE | ISO TEST METHOD | UNITS (SI) | VALUE |
|---|-----------------------|-------------------------------|---------|-----------------|-------------------------|-------|
| MECHANICAL | | | | | | |
| Tensile Strength @ Yield | ASTM D882 | psi | 8500 | ISO 527 | MPa | 62 |
| Ultimate | ASTM D882 | psi | 9000 | ISO 527 | MPa | 65 |
| Tensile Modulus | ASTM D882 | psi | 300000 | ISO 527 | MPa | 2100 |
| Tensile Elongation at Break | ASTM D882 | % | 100-160 | ISO 527 | % | 100 |
| Gardner Impact Strength at 0.03" (0.75 mm) | ASTM D3029 | ft-lb | 23 | ISO 6603-1 | J | 31 |
| Tear Strength | | | | | | |
| Initiation | ASTM D1004 | lb/mil | 1.4-1.8 | | kN/m | 245 |
| Propagation | ASTM D1922 | g/mil | 30-55 | | kN/m | 10-20 |
| Puncture Resistance (Dynatup) | ASTM D3763 | ft-lb | 9 | | J | 12 |
| Fold Endurance (MIT) | | | | | | |
| 0.010" (0.25 mm) | ASTM D2176-69 | double folds | 60 | | | |
| 0.020" (0.50 mm) | ASTM D2176-69 | double folds | 20 | | | |
| THERMAL | | | | | | |
| Coefficient of Thermal Conductivity | ASTM D5470 | Btu/hr/ft ² /°F/in | 1.35 | | W/m ² °K | 0.2 |
| Coefficient of Thermal Expansion | ASTM E831 | (x10 ⁻⁵ /°F) | 3.2 | ISO 11359 | (x10 ⁻⁵ /°C) | 7 |
| Specific Heat @40°F (4°C) | ASTM E1269 | Btu/lb/°F | 0.3 | | KJ/Kg-°C | 1.25 |
| Glass Transition Temperature | ASTM D3417 / D3418 | °F | 307 | ISO 11357 | °C | 153 |
| Vicat Softening Temperature, B | ASTM 1525-00 modified | °F | 323 | | °C | 150 |
| Heat Deflection Temp. by TMA at 1.8 Mpa | | °F | 290 | ISO 75 Modified | °C | 135 |
| Brittleness Temperature | ASTM D746 | °F | -211 | | °C | -135 |
| PHYSICAL | | | | | | |
| Density | ASTM D792 | slug/ft ³ | 2.3 | ISO 1183 | kg/m ³ | 1200 |
| Water Absorption, 24 hrs. | ASTM D570 | % change | 0.35 | ISO 62 | % change | 0.35 |
| Surface Energy(1 st surface/ 2 nd surface) | ASTM D5946-01 | - | 38/32 | | | |
| Surface Tension(1 st surface/ 2 nd surface) | Dyne Pens | Dyne | >44/>44 | | | |

| PROPERTY | ASTM TEST METHOD | UNITS (USCS) | VALUE | ISO TEST METHOD | UNITS (SI) | VALUE |
|-------------------------------------|------------------|--------------|-------|-----------------|------------|-------|
| OPTICAL | | | | | | |
| Refractive Index @77°F (25°C) | ASTM D542A | - | 1.6 | | | |
| Light Transmission | ASTM D1003 | % | 85 | | | |
| Yellowness Index | ASTM D1925 | % | 2 | | | |
| Haze | ASTM D1003 | % | 102 | | | |
| Gloss over Flat Black min/max @ 60° | ASTM D523-60 | - | 4 | ISO 2813 | - | 4 |

◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC representative or the SABIC Quality Services Department. Reported values are based on 0.250 mm (0.010") thickness film unless otherwise noted.
 ™ Trademark of SABIC.

MANUFACTURING SPECIFICATIONS

| NOMINAL GAUGE RANGES | MIN./MAX LIMIT OF NOMINAL |
|----------------------------------|---------------------------|
| 0.010 - 0.015" (0.250 - 0.375mm) | ± 5% |
| 0.020" (0.500 mm) | ± 3% |

Distributed by:



www.polymerfilms.com

Film East: Tyngsboro, MA | 978-226-0021
Film Central: Naperville, IL | 630-428-4350
Film West: Fresno, CA | 559-383-3456
Film Canada: Brampton, ON | 905-789-3100
Film Mexico: Apodaca, Nuevo León | 52-81-8369-4688

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.
 © 2014 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

† Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.



LEXAN is a trademark of SABIC