

LEXAN™ HC23 FILM

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ HC23 Film, is a white thermoplastic film that is a blend of polybutylene terephthalate and polycarbonate. It has outstanding printability and good dimensional stability at elevated temperature.

TYPICAL PROPERTY VALUES◆

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
MECHANICAL						
Tensile Strength @ Yield	ASTM D882	Psi	8724	ISO 527	MPa	60.2
Ultimate	ASTM D882	psi	9203	ISO 527	MPa	63.5
Tensile Modulus	ASTM D882	psi	348260	ISO 527	MPa	2403
Tensile Elongation at Break	ASTM D882	%	128	ISO 527	%	128
Izod Impact, unnotched, 23°C/3.2mm	ASTM D4812	ft-lb	5.1		J	6.9
Izod Impact, notched, 23°C/3.2mm	ASTM D256	ft-lb	0.25		J	0.33
Puncture Resistance (Dynatup)	ASTM D3763	ft-lb	4.6		J	6.26
THERMAL						
Coefficient of Thermal Conductivity	ASTM E1461	Btu/hr/ft ² /°F/in	2.54		W/m°K	0.32
Coefficient of Thermal Expansion	ASTM E831	(x10 ⁻⁵ /°F)	4.4	ISO 11359	(x10 ⁻⁵ /°C)	8
Glass Transition Temperature	ASTM D3417 / D3418	°F		ISO 11357	°C	
Vicat Softening Temperature, B	ASTM 1525-00 modified	°F	269.6		°C	132
Heat Deflection Temp. by TMA at 1.8 Mpa		°F	226.4	ISO 75 Modified	°C	108
Shrinkage at 266°F (130°C)	ASTM D1204	%	1.06/0.76			1.06/0.76
Shrinkage at 302°F (150°C)	ASTM D1204	%	1.56/1.24		%	1.56/1.24
PHYSICAL						
Density	ASTM D792	slug/ft ³	2.4	ISO 1183	kg/m ³	1.24
Water Absorption, 24 hrs.	ASTM D570	% change	0.04	ISO 62	% change	0.04
Surface Energy(1 st surface/ 2 nd surface)	ASTM D5946-01	-	36/35			
Surface Tension(1 st surface/ 2 nd surface)	Dyne Pens	Dyne	>36/34-36			
OPTICAL						
Color: L/a/b	CIE Lab 1976		91.9/-1.5/1.9			
Gloss over Flat Black fine matte @ 60°	ASTM D523-60	-	9	ISO 2813		9
ELECTRICAL						
Volume Resistivity	ASTM D257	Ω-cm	1.8E+16	IEC 60093	Ω-cm	1.8E+16
Surface Resistivity	ASTM D257	Ω/square	1.2E+16	IEC 60093	Ω/square	1.2E+16

◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC Innovative Plastics representative or SABIC Quality Services Department. Reported values are based on 0.35 mm (0.014") thickness film unless otherwise noted.

™ Trademark of SABIC

MANUFACTURING SPECIFICATIONS

NOMINAL GAUGE RANGES	MIN./MAX LIMIT OF NOMINAL
0.007 - 0.010" (0.175 mm-0.250 mm)	+/-10%
0.014 - 0.020" (0.350 - 0.500mm)	+/-5%

Color code:

White Color - WH9G037 (WH)

Distributed by:



www.polymerfilms.com

Film East: Tyngsboro, MA | 978-226-0021
Film Central: Naperville, IL | 630-428-4350
Film West: Fresno, CA | 559-383-3456
Film Canada: Brampton, ON | 905-789-3100
Film Mexico: Apodaca, Nuevo León | 52-81-8369-4688

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with TM are trademarks of SABIC or its subsidiaries or affiliates.
© 2014 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

¹Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.



LEXAN is a trademark of SABIC