

# LEXAN™ SD14UV FILM

## PRODUCT DATASHEET

### DESCRIPTION

LEXAN™ SD14UV Film is a one side fine velvet (FV), one side fine matte (FM) clear transparent laser markable polycarbonate overlay film that is typically used in government security documents, such as passport data pages, ID cards, driving licenses, ... Beside great printability and ease of processing (laminating, die-cutting, hot stamping), it offers the possibility to apply personalized security features into the card by use of UV laser marking. LEXAN™ SD14UV Film is available in 50 and 100µm.

### TYPICAL PROPERTY VALUES

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
<b>MECHANICAL</b>						
Tensile Strength @Yield	ASTM D882	psi	7830	ISO 527	MPa	54
@Break	ASTM D882	psi	9700	ISO 527	MPa	67
Tensile Modulus	ASTM D882	psi	300 x10 <sup>3</sup>	ISO 527	MPa	2080
Tensile Elongation at Break	ASTM D882	%	137	ISO 527	%	137
<b>THERMAL</b>						
Coefficient of Thermal Expansion, flow	ASTM E831	(x 10 <sup>-5</sup> / °F)	4.2	ISO 11359	(x 10 <sup>-5</sup> / °C)	7.5
Vicat Softening Temperature, B50	ASTM 1525	°F	295	ISO 306	°C	147
Shrinkage at 130°C, 30min	Internal method	%	0.17	Internal method	%	0.17
<b>PHYSICAL</b>						
Density	ASTM D792	slug/ft <sup>3</sup>	2.33	ISO 1183	g/cm <sup>3</sup>	1.20
Water Absorption, 24 hrs.	ASTM D570	% change	0.09	ISO 62	% change	0.09
Surface Roughness Ra		µin	23[FM]	ISO4288	µm	0.6 [FM]
			102[FV]			2.6[FV]
Surface Tension	Dyne solutions	Dyne/cm	44 [FM]	Dyne solutions	Dyne/cm	44 [FM]
			38 [FV]			38 [FV]
<b>OPTICAL</b>						
Light Transmission	ASTM D1003	%	84	ASTM D1003	%	84
Color: b-value	CIELab, Reflection, D65, 10°		3.26	CIELab, Reflection, D65, 10°		3.26

◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC, Specialty Film & Sheet representative or the Quality Services Department. Reported Values are based on 0.100 mm (0.004") thickness film, except for the Coefficient of thermal expansion, Vicat softening temperature, Heat deflection temperature and water absorption, which are based on molded parts.

™ Trademark of SABIC.

---

## MANUFACTURING SPECIFICATIONS

---

NOMINAL GAUGE RANGES	MIN./MAX LIMIT OF NOMINAL
0.050 and 0.100 mm	± 5%

---

Distributed by:



[www.polymerfilms.com](http://www.polymerfilms.com)

**Film East:** Tyngsboro, MA | 978-226-0021  
**Film Central:** Naperville, IL | 630-428-4350  
**Film West:** Fresno, CA | 559-383-3456  
**Film Canada:** Brampton, ON | 905-789-3100  
**Film Mexico:** Apodaca, Nuevo León | 52-81-8369-4688

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.  
© 2017 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

<sup>1</sup> Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

Rev. 30/05/2017

---