

VALOX™ FR1 FILM

PRODUCT DATASHEET

DESCRIPTION

VALOX™ FR-1 film is a flame retardant thermoplastic polybutylene, terephthalite film offering UL94 VTM-0 performance down to 130 microns and good temperature performance. VALOX FR-1 film's outstanding dielectric strength and ease of fabrication (ie: thermoforming, embossing, clean-edge die-cutting, folding and bending) makes it very suitable for a wide range of electrical, electronic and medical applications.

TYPICAL PROPERTY VALUES

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
MECHANICAL						
Tensile Strength @ Yield	ASTM D882	psi	7200	ISO 527	MPa	49.7
Ultimate	ASTM D882	psi	6000	ISO 527	MPa	41.1
Tensile Modulus	ASTM D882	psi	277000	ISO 527	MPa	1910
Tensile Elongation at Break	ASTM D882	%	57	ISO 527	%	57
Gardner Impact Strength at 0.03" (0.75 mm)	ASTM D3029	ft-lb	7	ISO 6603-1	J	10
Tear Strength						
Initiation	ASTM D1004	lb/mil	1.46		kN/m	255
Propagation	ASTM D1922	g/mil	55		kN/m	20
Puncture Resistance (Dynatup)	ASTM D3763	ft-lb	9		J	12
Fold Endurance (MIT)						
0.007" (0.175 mm)	ASTM D2176-69	double folds	2000			
0.020" (0.625 mm)	ASTM D2176-69	double folds	83			

THERMAL						
Coefficient of Thermal Conductivity	ASTM D5470	Btu/hr/ft ² /°F/in	1.35		W/m°K	0.17
Coefficient of Thermal Expansion	ASTM E831	(x10 ⁻⁵ /°F)	3.1	ISO 11359	(x10 ⁻⁵ /°C)	5.7
Specific Heat @40°F (4°C)	ASTM E1269	Btu/lb/°F	0.3		KJ/Kg-°C	1.31
Glass Transition Temperature	ASTM D3417 / D3418	°F	183	ISO 11357	°C	84
Vicat Softening Temperature, B	ASTM 1525-00 modified	°F	346		°C	174
Heat Deflection Temp. by TMA at 1.8 Mpa		°F	174	ISO 75 Modified	°C	79
Shrinkage at 302°F (150°C)	ASTM D1204	%	0.40		%	0.40
Brittleness Temperature	ASTM D746	°F	-211		°C	-135

PHYSICAL						
Density	ASTM D792	slug/ft ³	2.6	ISO 1183	kg/m ³	1340
Water Absorption, 24 hrs.	ASTM D570	% change	0.48	ISO 62	% change	0.48
Surface Energy(1 st surface/ 2 nd surface)	ASTM D5946-01	-	36/35			
Surface Tension(1 st surface/ 2 nd surface)	Dyne Pens	Dyne	>44/34-36			
Pencil Hardness	ASTM D3363	-	2b-b			

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
OPTICAL						
Light Transmission	ASTM D1003	%	15			
Yellowness Index	ASTM D1925	%	49			
Haze	ASTM D1003	%	103			
Gloss over Flat Black min/max @ 60°	ASTM D523-60	-	5	ISO 2813		5
ELECTRICAL						
Dielectric Strength in oil, short time @ 72°F (23°C), 10 mils (0.25mm)	ASTM D 149-97a Method A	kV/mil	1.09	IEC 60243	kV/mm	43
Dielectric Constant						
@ 60 Hz	ASTM D150	-	3.3	IEC 60250	-	3.3
@1,000,000 Hz	ASTM D150	-	2.8	IEC 60250	-	2.8
Dissipation Factor						
@ 60 Hz	ASTM D150	-	0.0015	IEC 60250	-	0.0015
@1,000,000 Hz	ASTM D150	-	0.01	IEC 60250	-	0.01
Volume Resistivity	ASTM D257	Ω-cm	1E+17	IEC 60093	Ω-cm	1E+17
Surface Resistivity	ASTM D257	Ω/square	1E+16	IEC 60093	Ω/square	1E+16
Arc Resistance, Tungsten Electrodes	ASTM D495	s	21			

◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC representative or the SABIC Quality Services Department. Reported values are based on 0.250 mm (0.010") thickness film unless otherwise noted.
 TM Trademark of SABIC.

GLOSS BY GAUGE: (ASTM D 523-85)

GAUGE	ANGLE		MATTE
.003" (0.075mm)	85°	Minimum	0.1
FR1	0.006 - 0.030" (0.150 - 0.750mm)	Maximum	25
		Minimum	0.1
		Maximum	17

MANUFACTURING SPECIFICATIONS

NOMINAL GAUGE RANGES	MIN./MAX LIMIT OF NOMINAL
0.003 – 0.010" (0.075 mm-0.250 mm)	-/+10%
0.015 - 0.030" (0.375 - 0.750mm)	-/+5%

Color Code:

Black Color – BK1066 (BK)

Natural Color – 1001 (NC)

UL File Number: [E121562](#), [E207780](#)

Distributed by:



www.polymerfilms.com

Film East: Tyngsboro, MA | 978-226-0021
Film Central: Naperville, IL | 630-428-4350
Film West: Fresno, CA | 559-383-3456
Film Canada: Brampton, ON | 905-789-3100
Film Mexico: Apodaca, Nuevo León | 52-81-8369-4688

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with TM are trademarks of SABIC or its subsidiaries or affiliates.
© 2014 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

[†] Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

