



TR3020C

Random Copolymer Polypropylene

- Clarified, High Flexural Modulus
- Suggested Uses Include Extrusion, Blow Molding, Thermoforming

Property	Units	Typical Value	Test Method
Nominal Melt Flow Rate (230°C/2.16kg)	g/10 min	2	ASTM D1238
Tensile Strength at Yield (2 in/min, 50 mm/min)	psi MPa	4,600 32	ASTM D638
Elongation at Yield (2 in/min, 50 mm/min)	%	12	ASTM D638
Flexural Modulus (0.05 in/min, 1.3 mm/min, 1% secant)	psi MPa	170,000 1,172	ASTM D790A
Notched Izod Impact Strength at 23°C	ft-lbs/in J/m	1.2 64	ASTM D256A

Distributed by:



www.polymerfilms.com

Film East: Tyngsboro, MA | 978-226-0021
Film Central: Naperville, IL | 630-428-4350
Film West: Fresno, CA | 559-383-3456
Film Canada: Brampton, ON | 905-789-3100
Film Mexico: Apodaca, Nuevo León | 52-81-8369-4688

Information contained herein is considered accurate to our best knowledge. It is offered for your consideration and investigation, and is not to be construed as a representation or warranty, expressed or implied, for which Sunoco Chemicals assumes legal responsibility. Our warranties are limited to those expressly stated in formal contracts or in conditions of sale on our invoices and order acceptances. Conditions and methods of use vary and are beyond the control of Sunoco Chemicals. Sunoco Chemicals, therefore, disclaims any liability incurred as a result of the use of its products in accordance with the data contained herein. No information herein shall be construed as an offer of indemnity for infringement or as a recommendation to use these products in such a manner as to infringe any patent, domestic or foreign.

For cautions and other information relating to handling of and exposure to this product, please see material safety data sheet code number C4027 published by Sunoco Chemicals.

550 Technology Drive
Pittsburgh, PA 15219
1-800-223-8871

Revision Date: 12/09/2008

www.sunocochemicals.com